

Meas.Nr. 61780 **Date** Freitag, 01 März 2013 10:56 **Personal Report No.:**
Material Glass short (in EtOH) 45min P5cl 400rpm 500ml ZrO2 **M130024**
Description predisp. in 0,1% Na4P2O7 with ultrasound LABORETTE 17

Calculation Fraunhofer broad **TradeOff** 1.000000e+002
Scans Fine 100 **Scans Coarse** 0 **Channels** 51 **Beam Obscuration** 16.00 %
Meas. Range 0.08 [µm] - 42.30 [µm] **Pump** 5 **Ultrasonics** 10

%	< µm
5	0.52
10	0.66
15	0.79
20	0.93
25	1.06
30	1.20
40	1.51
50	1.88
60	2.33
70	2.87
80	3.60
90	4.75
95	5.78
98	7.00
99	7.79

%	< µm
0.0	0.1
4.5	0.5
22.8	1.0
39.6	1.5
52.8	2.0
72.0	3.0
84.1	4.0
91.4	5.0
95.8	6.0
98.0	7.0
99.2	8.0
99.9	10.0
100.0	12.0
100.0	15.0
100.0	22.0

