

Meas.Nr.	61754	Date	Donnerstag, 28 Februar 2013 05:07	Personal Report No.:
Material	Glass short (in EtOH)		30min P5cl 400rpm 500ml ZrO2 10mm	M130024
Description	predisp. in EtOH + 1min Ultrasonic LABORETTE 17			

Calculation	Fraunhofer	broad	TradeOff	1.000000e+003
Scans Fine	100	Scans Coarse	100	Channels
				102
Beam Obscuration	15.00 %			
Meas. Range	0.08 [µm]	- 2000.00 [µm]	Pump	7
			Ultrasonics	10

%	< µm
5	0.64
10	0.92
15	1.20
20	1.51
25	1.84
30	2.21
40	3.16
50	4.50
60	6.42
70	9.01
80	12.38
90	17.26
95	21.40
98	26.05
99	29.14

%	< µm
0.0	0.1
2.7	0.5
11.4	1.0
27.2	2.0
38.5	3.0
46.7	4.0
58.1	6.0
66.4	8.0
73.2	10.0
79.0	12.0
86.0	15.0
93.6	20.0
99.2	30.0
100.0	40.0

